

# DUROPROOF ATC

Provides Greater UV Protection & Colour Fastness For Membranes



## DESCRIPTION

Duroproof ATC is single pack, aliphatic polyurethane waterproofing top coat which has been formulated as a complimentary and compatible top coat for UV Compatible Polyurethane membranes. Aliphatic technology provides greater UV protection, colour fastness and anti-chalking properties and is designed to extend the life of exposed aromatic polyurethanes. Duroproof ATC forms a tough, flexible, seamless, highly UV stable, waterproof coating. Duroproof ATC meets the 'Green Star' environmental criteria.

## FEATURES

ATC represents the highest standards in aliphatic polyurethane waterproofing technology and provides the following benefits and advantages:

- Provides excellent UV protection.
- Extends the life of the waterproofing membrane system.
- Meets the 'Green Star' environmental criteria.
- Single pack - no mixing.
- Curing (usually within) 24 hours.
- Permanently flexible
- Good chemical resistance.
- High strength and puncture resistant.
- Provides seamless membrane (no joints or laps)
- Easily repaired and or maintained.
- Easy to apply.
- Can withstand light foot traffic.

## USE AREA

ATC is primarily formulated as a highly UV stable top coat over Compatible Polyurethane membranes to give greater long term UV protection and colour fastness thereby extending the life and performance of the waterproofing membrane.

## TECHNICAL INFORMATION

<b>Appearance (dry film)</b>	Grey, glossy
<b>Tack-free Time</b>	8 hours at 25°C & 50% R.H. , 0.15 mm film.
<b>Cure</b>	24 hours. Light foot traffic only after 24 hours.
<b>Weather Resistance</b>	2000 hours QUV, no crazing, spalling or softening.
<b>Solids Content</b>	80%
<b>Tensile Strength Max.</b>	7.0 Mpa, AS/NZS 1683.11
<b>Elongation at break</b>	270%, AS/NZS 1683.11
<b>Tear Strength</b>	28 N/cm, ASTM D-1004
<b>Hardness</b>	68 Shore A. AS 1683.15
<b>Abrasion Resistance</b>	0.1mm depth, 500 cycles, CS-10 wheel, AS1580.403.2 (non-trafficable)
<b>Chemical Resistance</b>	No visible effect, 16 hrs, 40°C: 20% detergent, auto coolant, kerosene, motor oil, caustic solution (pH 13.5)





## LIMITATIONS

Suitable for maintenance foot traffic and not intended as a general trafficable membrane.

## PRECAUTIONS IN USE

Risk is considered low when properly used but precautions on can, label and / or data sheets should be observed. Do not use in confined areas with poor ventilation. Uncured product is flammable.

## PRIMING AND SURFACE PREPARATION

Good preparation is essential. Surfaces must be sound, stable, dry, clean and free of dust, loose, flaking, friable material and substances that may diminish adhesion.

As its main purpose is to be applied over cured Polyurethane Membrane, it can be applied as follows:

Providing the existing membranes are clean, dry and that the Duroproof ATC is being applied within 48 hours of applying the Duroproof membranes - no other preparation is required.

## SUITABLE SURFACES

ATC have been formulated as top coat over Polyurethane Membrane.

## SPECIFICATION

The information contained in this product data sheet is typical but does not constitute a full specification as conditions and specific requirements may vary from project to project. The instructions should be considered as a minimum requirement but the applicator or contractor must use their skill, knowledge and experience to carry out additional works as may be necessary to meet the requirements of the project. Specification for specific projects should be sought from the company in writing.

When dry check for pin holes or misses and rectify if necessary.

## SLIP RESISTANT FINISH

The following slip resistance rating was achieved by broadcasting 250gms of Durogrit aggregate per square metre of applied Duroproof ATC.

TEST	RATING	TEST METHOD
Dry Friction (with Durogrit)	D1	(AS 4586)
Wet Friction (with Durogrit)	P5	(AS 4586)

## APPLICATION

Apply ATC to Polyurethane Membrane by brush, roller, broom and squeegee usually in one or two coats at the rate of 3m<sup>2</sup> per litre per coat, so that the minimum dry film thickness is 300 microns.

## COVERAGE

The stated average coverage rate may vary depending upon type, condition, porosity, texture of the surface and application technique.

ATC Top Coat: Generally, 3m<sup>2</sup> per litre per coat.

## DRYING AND CURING

Drying and curing of the product is affected by type, dryness and porosity of the surface, temperature, humidity, ventilation, climate conditions and application technique and therefore drying and curing can only be given as a guide.

Generally Duroproof ATC is weather resistant within 6 to 8 hours with full cure within 24 hours.

## STORAGE

Keep in cool, dry place away from heat, flame, combustible material and all sources of ignition. Product contains flammable solvents. Class 3 dangerous goods must be declared prior to transportation. Available in 15 Lt pails.

Self life: 6 - 12 months in unopened container but best used within 6 months. As this is a polyurethane some skinning of the product may occur. This should be cut out and removed. Balance of the product will be suitable for use.

## CLEAN UP

Avoid spills. They are difficult to clean particularly off porous surfaces. Wet spills use a cloth and Duroproof Solvent. Do not clean off carpets as it is better to allow product to cure and then shave the carpet. Equipment should be immediately cleaned with Duroproof Solvent.

## TILING, TOPPING OR TOP COATING

Generally not covered, although membrane may be covered with drainage cloth and pebbles, ensuring not to damage membrane.

## SAFETY & PRECAUTIONS

Duroproof ATC is solvent based. The use of solvent resistant gloves and goggles (against splashes) are recommended. Use in ventilated areas. If spraying, in confined areas the use of self contained breathing apparatus is recommended. If swallowed do not induce vomiting, give plenty of water to drink. Seek urgent medical advice. If in eyes, flush thoroughly with clean water, holding open lid to ensure any trapped product may be flushed away. If on skin, remove contaminated clothing and wash skin with soap and water.

If inhaled, unlikely due to viscosity of the product, remove person to fresh air and apply artificial respiration if required and seek urgent medical attention. Product is flammable when wet. Keep away from all sources of ignition. Ensure adequate ventilation. Vapours may collect in low lying areas.

Not suitable for use in areas of ponding water. Do not allow ponding to occur between coats or before system is fully cured.

For full safety data refer to the products Material Safety Data Sheet. Observe precautions as per label.

### VICTORIA

34 Indian Drive Keysborough  
Victoria 3173  
Tel: 1300 434 272  
sales@durotechindustries.com.au  
www.durotechindustries.com.au

### NEW SOUTH WALES

14 Essex st, Minto, Sydney  
NSW 2566  
Tel: 1300 434 272  
sales@durotechindustries.com.au  
www.durotechindustries.com.au

### QUEENSLAND

1/16 Export Drive, MOLENDINAR  
QLD 4214  
Tel: 1300 434 272  
sales@durotechindustries.com.au  
www.durotechindustries.com.au

### SOUTH AUSTRALIA

30C Richard Street  
Hindmarsh, SA, 5007  
Tel: 1300 434 272  
sales@durotechindustries.com.au  
www.durotechindustries.com.au

"This document, including any attached files, is strictly confidential and intended solely for the use of the individual or entity to which it is addressed. Durotech Industries prohibits the right to publish, copy, distribute or disclose any information contained in this document, or its attachments, by any party other than the intended recipient. If you have received this document in error please notify the sender and delete it from your system no employee or agent is authorised to conclude any binding agreement or make any representation on behalf of Durotech Industries. The views or opinions presented in this document are solely those of the author and do not necessarily represent those of Durotech Industries, except where the sender expressly, and with clear authority, states them to be the views of Durotech Industries. Durotech Industries accepts no liability for any loss or damage (direct or indirect or consequential) arising from the use of or in connection with this document and any attachments and suggests that the recipient check this document and any attached files for the presence of viruses."

