

DUROMASTIC BLW

FOR RETAINING WALLS & PLANTER BOXES



DESCRIPTION

Duromastic BLW is a liquid applied, latex modified bituminous elastomeric waterproofing membrane which, when fully cured, forms a permanently flexible waterproof lining to most building surfaces including reinforced concrete, block work, brick work and cement render.

FEATURES

- Single component, user friendly.
- Simple application – brush, roller or spray
- Excellent elasticity.
- Seamless
- Environmentally friendly
- Non-toxic water based
- Fast curing

USE AREA

- Retaining walls and underground surfaces
- External cellar and basement walls
- Planter boxes and garden beds
- Gutter repairs
- Roofing and membrane repairs
- Protective coating over metal and timber surfaces

PACKAGING

- 15 Litre

TECHNICAL INFORMATION

Colour	Purple when wet, dries black
Weather resistance	Should be protected from sunlight
Drying	Tack Free: 60-90 minutes Re-coat: 2-4 hours
Based on normal ambient temperatures of 23°C and 50% RH	Dry film – 24 hours Backfill: 5 days curing Flood test: 10 days curing
*Temperature, humidity and porosity will vary dry times	
Re-coat time	4-6 hours @ 25°C
Coverage	Masonry – 1.8 – 2.0L/m ² or 3 coats @ 0.6L/m ² each Concrete – 1.5 – 1.8L/m ² or 2 coats @ 0.9L/m ² each
Wet film per coat	0.9mm thick
Dry film thickness	1.0mm minimum
Solids content	58% by volume
Shelf life	12 months in unopened container @ 20°C





SURFACE PREPARATION

Concrete must be cured for a minimum of 28 days and render 7 days. Remove dirt, dust, loose particles, oil and unsound concrete etc. Water blast if necessary. Surface must be dry. Fill holes and open joints in block work or concrete prior to application of membrane.

PRIMING

Duromastic BLW is self priming when used on most surfaces e.g. Sound concrete, block work. Surfaces may be primed with Duromastic BLW thinned with 50% water or with Durotech AR Sealer. Areas subject to rising damp should be first sealed with an epoxy coating, such as Duromix Hibuild WBE.

BOND BREAKERS

Apply a bead of Duroseal hybrid sealant to the following areas: Wall/ footing junction where movement is expected and expansion joints, generally to all areas where movement is likely to occur.

INSTALLATION OF DUROFABRIC JOINT SEAL TAPE

Measure and cut Durofabric Joint seal Tape for all wall and floor junctions. The first coat of Duromastic BLW to be applied approximately 150mm up the wall and on to the floor, in which the Durofabric Joint Seal Tape is embedded. Install the Joint Seal Tape into wet bed of membrane, ensuring the fabricated edges are completely wet out and critical that no air bubbles exist behind the Joint Seal Tape.

APPLICATION

Reinforced: To the prepared surface apply a heavy coat of Duromastic BLW by brush or roller at approximately 2m²/litre. Immediately lay the reinforcing fabric into the wet surface, then apply another coat and work in carefully by brush or roller to saturate the fabric. When dry apply one or more coats to give a fully waterproof lining. Ensure a minimum coverage of 1.6 Litre/m². When dry, check for pinholes or misses and re-coat if necessary.

Un-reinforced: To areas where a reinforcing fabric is not utilized apply 3 coats of Duromastic BLW at a total rate of 1.8 Litre/m² ensuring full coverage by brush, roller or spray (use 21 thou Min tip size + airless spray).

Porous Surface (Masonry): May require 3 coats to obtain a satisfactory dry film thickness.

CLEANING

Clean with water before dry.

PRECAUTIONS

Do not apply above 30°C or below 10°C ambient temperature. Be sure coating will cure before contact with water. Wash equipment with water before dry. Protect Duromastic BLW from extended sunlight exposure. Planter box membrane must be fully cured before being subject to moisture or soil. Protect membrane against damage before and during backfilling or covering. Durotech protection board may be used where suitable. Use an approved drainage system and protection board in planter boxes and retaining walls before filling to protect membrane from any damage. Do not expose to solvents.

VICTORIA

34 Indian Drive Keysborough
Victoria 3173
Tel: 1300 434 272
sales@durotechindustries.com.au
www.durotechindustries.com.au

NEW SOUTH WALES

14 Essex st, Minto, Sydney
NSW 2566
Tel: 1300 434 272
sales@durotechindustries.com.au
www.durotechindustries.com.au

QUEENSLAND

1/16 Export Drive, MOLENDINAR
QLD 4214
Tel: 1300 434 272
sales@durotechindustries.com.au
www.durotechindustries.com.au

SOUTH AUSTRALIA

30C Richard Street
Hindmarsh, SA, 5007
Tel: 1300 434 272
sales@durotechindustries.com.au
www.durotechindustries.com.au

