

DUROFLEX™ TANK

POLYMER CEMENTITIOUS MEMBRANE



DESCRIPTION

DUROFLEX™ TANK is a two component polymer modified cementitious coating designed for waterproofing concrete and masonry surfaces in a variety of applications. Designed for use in wet and damp conditions including applications such as:

- Internal wet areas, bathrooms, laundries and tiled areas
- Balconies, decks, podiums and terrace floors
- Parapet and feature walls
- Planters and retaining walls
- Water features and tanks

Based on unique cross linking polymer technology, DUROFLEX™ TANK displays outstanding adhesion properties over numerous building substrates including concrete, masonry, renders, screeds and cement based mineral surfaces. No priming is required as DUROFLEX TANK bonds to clean pre-dampened surfaces free of surface water. For applications where finishes need to be applied over this membrane, tiles, renders, textures and solvent free paints are able to be directly applied to the cured DUROFLEX™ TANK surface.

FEATURES

- Flexible with good elongation properties
- Can be applied on vertical and horizontal surfaces
- Bonds to concrete surfaces after 48 hours of application; bonds to renders, screeds etc after 16 hours of application
- Compatible bonding properties for tile adhesives, screeds, renders and texture coatings

TECHNICAL INFORMATION

Wet Form

Specific Gravity of Mixed Product 1.4kg/litre

Appearance Liquid - white; powder - sandy;
Mixed - cement grey

Cured Membrane Mid Grey Flexible Film

Tensile Strength >1.4MPa

Adhesion to Concrete >1.5MPa

Shore A Hardness 68

PACKAGING

- Part A - 20 kg powder and Part B - 10 litre resin



GENERAL APPLICATION DETAILS

- Surfaces must be clean, suitably prepared and in a sound state prior to beginning the application. Substrates do not require to be primed however surfaces must be damp or pre-wetted ensuring that they are free of surface or ponding water.
- For movement joints DUROFABRIC™ JOINT SEAL TAPE is to be applied over joints followed by the application of DUROFLEX™ TANK. For non-movement cracks, these are to be filled first with DUROFLEX™ TANK and reinforced using DURO RF FABRIC prior to over coating with membrane. For waterproofing applications on the positive sides, wall/ floor junctions are to be protected with the DUROFABRIC™ JOINT SEAL TAPE embedded into the coat of DUROFLEX™ TANK. For negative applications a waterproof fillet is recommended to be used at junctions using DUROFLEX™ PLUG.
- DUROFLEX™ TANK membrane is formed by mixing 1 litre of Part B liquid to 2 kg of Part A dry, or full unit mix of 10 litres of Part B to 20kg of Part A. An electric stirrer and paddle is recommended to be used to ensure a homogenous state is formed. Starting with a slow mixing speed, the powder component should be slowly added to the liquid, increasing the mixing speed as the powder addition increases. Mixing should continue until product is consistent and lump free, then allow product to settle for a few minutes before restirring lightly. DUROFLEX™ TANK will then be ready to use.
- First coat is to be applied at a coverage of 1L/m² (approx. 1 Litre of mixed compound) using a roller or trowel at a nominal 1mm wet film thickness. Allow first coat to dry which may take 30-60 minutes depending on surface porosity and ambient conditions. Once touch dry apply second coat at right angles to the first coat, repeating the coverage of the first coat of 1L/m² at 1mm(min thickness). Subsequent coats can be applied if required. .

IMPORTANT NOTES

- Pot life for the mixed membrane is approximately 45-60 minutes in normal ambient conditions of < 20°C

Drying times are :

- Recoat 1-2hours
- Dry time 6-8hours
- Immersion 21 days

Based on normal ambient conditions of 20 C

- Allow 48 hours drying before applying light foot traffic over the DUROFLEX™ TANK. For immersed areas, allow 5 - 7 days drying prior to filling. A light wash down and removal of first water is recommended prior to filling for intended purpose.
- For applications where renders or screeds are applied over the membrane, ensure these compounds are enhanced with an additive such as Duro additive or acrylic/latex bonding additives. DUROTILE™ PRO tile adhesive is recommended for direct adhesion of tiles to DUROFLEX™ TANK.
- Best storage conditions for liquid and dry components is in a dry area at room temperature, avoiding humidity and frost. While in a wet state DUROFLEX™ TANK will clean up with water.
- Once dried product will need to be removed by mechanical means or with solvent cleaners.
- Application temperature and or surface temperature should be a minimum 5°C and maximum 30°C.

SHELF LIFE

- Shelf life Powder: 6 months in unopened container
- Shelf life Liquid: 6 months in unopened container

VICTORIA

34 Indian Drive Keysborough
Victoria 3173
Tel: 1300 434 272
sales@durotechindustries.com.au
www.durotechindustries.com.au

NEW SOUTH WALES

1 Prince William Drive, Seven Hills,
NSW, 2147
Tel: 1300 434 272
sales@durotechindustries.com.au
www.durotechindustries.com.au

QUEENSLAND

1/16 Export Drive, MOLENDINAR
QLD 4214
Tel: 1300 434 272
sales@durotechindustries.com.au
www.durotechindustries.com.au

SOUTH AUSTRALIA

30C Richard Street
Hindmarsh, SA, 5007
Tel: 1300 434 272
sales@durotechindustries.com.au
www.durotechindustries.com.au

