

DUROPRIME™ SSP PRO



DESCRIPTION

DUROPRIME™ SSP PRO is a one-part waterbased, high performance primer designed for priming non-porous, very dense and difficult to adhere to substrates. It dries into a gritty textured keyed finish, which provides excellent intercoat adhesion of the subsequent coatings or tile adhesives like DUROTILE PRO.

FEATURES

- Single component which easily spreads and is quick drying
- Enhances adhesion and bond of the waterproofing membranes to the non-porous substrate
- Excellent wetting and adhesion properties
- Non-flammable and environmentally safe
- Easy application with brush or roller
- Water resistant - suitable for use in wet areas

USE AREA

Suitable for priming:

- Walls and floors
- Exterior and interior applications.
- Wet areas

PACKAGING

- 5 Litre
- 10 Litre

TECHNICAL INFORMATION

Appearance when dry Fine Texture Blue

Odour Mild

Solid Content (Weight) 54%

Solid Content (Volume) 43%

Density 1.23 kg/li

Tack Free Time (@ 25 C) 30 - 40 minutes

Recoat Time 1 - 2 Hours

Film Hardness (Pencil) 3H

SUBSTRATES

- Metals including: galvanised iron, zincalume, aluminium, stainless steel, copper, brass treated steel, colorbond sheeting
- Existing ceramic glazed tiles, smooth and non-porous surfaces
- PVC and rigid plastic surfaces
- Compressed sheeting like Scyon™, MULTIPANEL™ and Dincel Structural Walling™

SURFACE PREPARATION

Surfaces must be clean, smooth, dry and free from laitance, grease, oil, wax, curing compounds, release agents, sealers, coatings, friable material or any loose contaminating material. Metal surfaces must be free from rust and oxidation film. Ensure all solvent or film residue is removed. All substrates' surfaces must be secure and continuous, all voids and gaps must be filled.



MIX PREPARATION

Ready-to-use (do not dilute).

APPLICATION

Apply one coat of the primer according to the recommended coverage rate with paintbrush or roller. Allow the primer to dry for a minimum of 1 hour and a maximum of 2 hours, at temperatures of 25°C and above; the primer must be touch dry. Longer drying times will be required at lower temperatures. Priming should only be carried out on surfaces which will be covered with membrane on the same day. Drying times will vary depending on humidity, surface temperature and porosity of substrates.

CLEAN-UP & RETURN TO SERVICE

Water can be used to clean up excess product, spills and tools while product is wet. When fully cured, tools and spills can be only removed mechanically or by solvent.

HEALTH & SAFETY PRECAUTIONS

DUOPRIME™ SSP PRO is a non-hazardous and non-dangerous product. The Safety Data Sheet (SDS) must be read and understood prior to use.

STORAGE CONDITIONS:

Store in dry, weatherproof environment, protected from direct sunlight at temperatures between +5°C and +25°C.

VICTORIA

34 Indian Drive Keysborough
Victoria 3173
Tel: 1300 434 272
sales@durotechindustries.com.au
www.durotechindustries.com.au

NEW SOUTH WALES

1 Prince William Drive, Seven Hills,
NSW, 2147
Tel: 1300 434 272
sales@durotechindustries.com.au
www.durotechindustries.com.au

QUEENSLAND

1/16 Export Drive, MOLENDINAR
QLD 4214
Tel: 1300 434 272
sales@durotechindustries.com.au
www.durotechindustries.com.au

SOUTH AUSTRALIA

30C Richard Street
Hindmarsh, SA, 5007
Tel: 1300 434 272
sales@durotechindustries.com.au
www.durotechindustries.com.au

"This document, including any attached files, is strictly confidential and intended solely for the use of the individual or entity to which it is addressed. Durotech Industries prohibits the right to publish, copy, distribute or disclose any information contained in this document, or its attachments, by any party other than the intended recipient. If you have received this document in error please notify the sender and delete it from your system no employee or agent is authorised to conclude any binding agreement or make any representation on behalf of Durotech Industries. The views or opinions presented in this document are solely those of the author and do not necessarily represent those of Durotech Industries, except where the sender expressly, and with clear authority, states them to be the views of Durotech Industries. Durotech Industries accepts no liability for any loss or damage (direct or indirect or consequential) arising from the use of or in connection with this document and any attachments and suggests that the recipient check this document and any attached files for the presence of viruses."



©DUROTECHINDUSTRIES.COM.AU